

Datasheet


Osiria seat of cm. 200

Product code 1135

Rev. 0 of 10/06/2016



1/5



Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

Datasheet

Osiria seat of cm. 200

Product code 1135

Rev. 0 of 10/06/2016



DESCRIPTION

Structure

Osiria bench composed of N. 2 shaped supports in galvanized steel sheet thickness mm. 6 with decorative carvings. Each single support is provided with plates at the base in galvanized sheet.

- Seat shell made with N. 2 external profiles in galvanized steel with rounded corners and n. 10 profiles in the internal part, in galvanized steel round tube of mm. 20x1.5 complete with PVC end caps with spherical head.

Overall weight: 45Kg

Datasheet

Osiria seat of cm. 200

Product code 1135


Rev. 0 of 10/06/2016



COLOR FINISH AS PROVIDED IN THE CATALOG



Gunmetal gray
(External supports and profiles)



Brilliant aluminum
(Internal seat profiles)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT VARIANTS



Product code 1135-BIS-PI - Osiria seat with wooden planks Nordic pine of cm. 180



Product code 1135-BIS -



Product code 1135-BIS-OK - Osiria seat with wooden planks Okumè of cm. 180

Datasheet

Osiria seat of cm. 200

Product code 1135

Rev. 0 of 10/06/2016



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment for removing oil and grease from metal surfaces using special degreasing liquids. Subsequent drying in dryer for 15 minutes.

Sandblasting

Manual sandblasting process with river sand, which increases the porosity of metal surfaces and thus the adhesion of thermosetting powders.

Anti-corrosive application

First painting cycle with an anticorrosive thermosetting powder primer based on epoxy resins and special pigments. It provides adequate protection against weathering.

Anticorrosive polymerization

Baking in an industrial curing oven at a temperature of 180°C. During this stage, the powder turns into a uniform, smooth and durable coating.

Colored finish application

Final coating cycle with thermosetting powders. Application follows the same principles as the anticorrosive.

Polymerization colored finish

Final baking in an industrial curing oven at a temperature of 180°C. The procedure follows the same principles as the curing of the anticorrosive. The powder is transformed into a uniform coating, and the surface appearance takes on the characteristics of the chosen color type, e.g. smooth, textured, wrinkled, etc.

4/5

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

Datasheet

Osiria seat of cm. 200

Product code 1135

Rev. 0 of 10/06/2016



DELIVERY

Product supplied in assembly kit with steel hardware and instructions for mounting and grounding.

FIXING

The product is prepared for fixing to the ground using anchor bolts and expansion plugs.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality management system.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate of Processing Center