
Rev. 0 of 10/06/2016









Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

+39 0833 95 50 13 WWW.DIMCAR.IT

INFO@DIMCAR.IT

VIA TAURISANO 101, Z.A. 73059 UGENTO (LE) ITALY P.I. C.F. 031129830752 REA LE 200574 CAP SOC. SOC. € 2.000.000.00

Rev. 0 of 10/06/2016



DESCRIPTION

Structure

Frame and rear arches made of round tubular galvanized steel Ø mm. 40x1.5.

- The frame is provided with galvanized sheet metal plates at the base. Shaped plate in the lower part.
- Reading surface in galvanized sheet metal thickness mm. 1.2 with perimeter edging in galvanized "U" profile.
- The perimeter edging allows the insertion and locking of the transparent compact polycarbonate panel thickness mm. 3.

Total weight: 16Kg

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

Rev. 0 of 10/06/2016



COLOR FINISH AS PROVIDED IN THE CATALOG



Gunmetal gray (Steel parts)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT OPTIONALS

Product code 191-PL -

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

Rev. 0 of 10/06/2016



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment for removing oil and grease from metal surfaces using special degreasing liquids. Subsequent drying in dryer for 15 minutes.

Sandblasting

Manual sandblasting process with river sand, which increases the porosity of metal surfaces and thus the adhesion of thermosetting powders.

Anti-corrosive application

First painting cycle with an anticorrosive thermosetting powder primer based on epoxy resins and special pigments. It provides adequate protection against weathering.

Anticorrosive polymerization

Baking in an industrial curing oven at a temperature of 180°C. During this stage, the powder turns into a uniform, smooth and durable coating.

Colored finish application

Final coating cycle with thermosetting powders. Application follows the same principles as the anticorrosive.

Polymerization colored finish

Final baking in an industrial curing oven at a temperature of 180°C. The procedure follows the same principles as the curing of the anticorrosive. The powder is transformed into a uniform coating, and the surface appearance takes on the characteristics of the chosen color type, e.g. smooth, textured, wrinkled, etc.

Rev. 0 of 10/06/2016



DELIVERY

FIXING

Product supplied in assembly kit with steel hardware and instructions for mounting and grounding.

The product is prepared for fixing to the ground using anchor bolts and expansion plugs.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality management system.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate of Processing Center

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.