


1/5



Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

---

## DESCRIPTION

### Structure

Flat bike rack for 5 places composed of 2 horizontal crosspieces in rectangular galvanized steel tube 50x30x2 mm complete with PVC end caps at the ends.

- The crosspieces are equipped with 8 feet that prevent direct contact of the structure with the ground.
- 5 arch-shaped bike-stop supports (welded to the two crosspieces) in 5 mm thick galvanized sheet metal characterized by a central hollowing that allows the wheel to be inserted and locked.
- N. 4 arch-shaped chain attachment supports (welded to the two crosspieces) in 5 mm thick galvanized sheet metal characterized by three stylised hollowing.

In order to allow practical and convenient use, the bike-stop supports and the chain attachment supports are arranged alternately with each other.

**Total weight:** 52Kg

---

**COLOR FINISH AS PROVIDED IN THE CATALOG**



RAL 2000  
( Steel parts )

Customers can request a different finish from the RAL color options available on our website.

---

## ANTICORROSIVE TREATMENTS AND FINISHES

### Washing

Spray treatment for removing oil and grease from metal surfaces using special degreasing liquids. Subsequent drying in dryer for 15 minutes.

### Sandblasting

Manual sandblasting process with river sand, which increases the porosity of metal surfaces and thus the adhesion of thermosetting powders.

### Anti-corrosive application

First painting cycle with an anticorrosive thermosetting powder primer based on epoxy resins and special pigments. It provides adequate protection against weathering.

### Anticorrosive polymerization

Baking in an industrial curing oven at a temperature of 180°C. During this stage, the powder turns into a uniform, smooth and durable coating.

### Colored finish application

Final coating cycle with thermosetting powders. Application follows the same principles as the anticorrosive.

### Polymerization colored finish

Final baking in an industrial curing oven at a temperature of 180°C. The procedure follows the same principles as the curing of the anticorrosive. The powder is transformed into a uniform coating, and the surface appearance takes on the characteristics of the chosen color type, e.g. smooth, textured, wrinkled, etc.

---

## DELIVERY

Product supplied already assembled with steel hardware and instructions for ground fixing.

---

## FIXING

The product is prepared for fixing to the ground using anchor bolts and expansion plugs.

---

## CORPORATE CERTIFICATIONS

### ISO 9001:2015

Quality management system.

### UNI EN ISO 3834-3:2021

Welding quality management system.

### Processing center

Certificate of Processing Center