

# Datasheet


Pin bollard stainless steel

Product code 601

Rev. 0 of 21/02/2023



1/5



Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

+39 0833 95 50 13

WWW.DIMCAR.IT

INFO@DIMCAR.IT

VIA TAURISANO 101, Z.A.  
73059 UGENTO (LE) ITALY

P.I. C.F. 031129830752

REA LE 200574 CAP SOC. SOC. € 2.000.000.00

# Datasheet

Pin bollard stainless steel

Product code 601

Rev. 0 of 21/02/2023



## DESCRIPTION

### Structure

Stainless steel bollard post model Pin. Made of circular section tubular Ø mm. 102x2, in brushed AISI 304 stainless steel, characterized by a cut in the terminal part with gradation, with closing cap in brushed AISI 304 stainless steel sheet thickness mm. 3. At the base, the bollard is complete with a flange in brushed AISI 304 stainless steel sheet thickness mm. 3 to cover the hole made for grouting.

**Total weight:** 6Kg

# Datasheet

Pin bollard stainless steel

Product code 601

Rev. 0 of 21/02/2023



---

## COLOR FINISH AS PROVIDED IN THE CATALOG

Customers can request a different finish from the RAL color options available on our website.

---

## PRODUCT OPTIONALS

Product code 601-AMOV - Removability system for Pin bollard in galvanized and painted steel

# Datasheet

Pin bollard stainless steel

Product code 601

Rev. 0 of 21/02/2023



## ANTICORROSIVE TREATMENTS AND FINISHES

### Washing

Spray treatment for removing oil and grease from metal surfaces using special degreasing liquids. Subsequent drying in dryer for 15 minutes.

### Sandblasting

Manual sandblasting process with river sand, which increases the porosity of metal surfaces and thus the adhesion of thermosetting powders.

### Anti-corrosive application

First painting cycle with an anticorrosive thermosetting powder primer based on epoxy resins and special pigments. It provides adequate protection against weathering.

### Anticorrosive polymerization

Baking in an industrial curing oven at a temperature of 180°C. During this stage, the powder turns into a uniform, smooth and durable coating.

### Colored finish application

Final coating cycle with thermosetting powders. Application follows the same principles as the anticorrosive.

### Polymerization colored finish

Final baking in an industrial curing oven at a temperature of 180°C. The procedure follows the same principles as the curing of the anticorrosive. The powder is transformed into a uniform coating, and the surface appearance takes on the characteristics of the chosen color type, e.g. smooth, textured, wrinkled, etc.

4/5

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

# Datasheet

Pin bollard stainless steel

Product code 601

Rev. 0 of 21/02/2023



---

## DELIVERY

Product supplied in assembly kit with steel hardware and instructions for mounting and grounding.

---

## FIXING

The product must be installed by cementing.

---

## CORPORATE CERTIFICATIONS

### ISO 9001:2015

Quality management system.

### UNI EN ISO 3834-3:2021

Welding quality management system.

### Processing center

Certificate of Processing Center