
Rev. 0 of 19/05/2021









Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

+39 0833 95 50 13 WWW.DIMCAR.IT

INFO@DIMCAR.IT

VIA TAURISANO 101, Z.A. 73059 UGENTO (LE) ITALY

Rev. 0 of 19/05/2021



DESCRIPTION

Structure

Alfy 3D letter made entirely of galvanized steel. Structure composed of a box, in 2 mm thick galvanized sheet metal, shaped with laser cutting technology, and an internal stiffening frame made of galvanized steel profiles. The structure is equipped at the base with extensions designed for grouting on a cement base. The Customer has the possibility of composing the writings as he likes (letters and numbers are provided in a single font with "Arial Narrow" characters).

Total weight: 92Kg

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

Rev. 0 of 19/05/2021



COLOR FINISH AS PROVIDED IN THE CATALOG



Customers can request a different finish from the RAL color options available on our website.

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

Rev. 0 of 19/05/2021



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

Rev. 0 of 19/05/2021



DELIVERY

FIXING

The product comes with an assembly kit that includes steel screws and instructions for mounting and fixing.

The product must be installed by cementing.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 14 Jan 2008

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles