

Rev. 0 of 24/03/2023









Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

# Datasheet Plomb

Product code D879

Rev. 0 of 24/03/2023



**DESCRIPTION** 

#### Structure

With its particular shape, the Plomb bike rack is made up of two shaped profiles, made of round galvanized steel tube Ø mm 60x2; the profiles are made integral with the base by a shaped plate, made of galvanized sheet metal thickness mm. 6 with laser cutting, and provided with holes for fixing to the ground.

- Shaped upper bracket, made of galvanized profile mm. 80x6, fixed to the round profiles with bolts.
- The shaped support is designed to be used on both sides, securing the bicycle to the support by means of a padlock.

Total weight: 18Kg

.

Rev. 0 of 24/03/2023



#### **COLOR FINISH AS PROVIDED IN THE CATALOG**



Customers can request a different finish from the RAL color options available on our website.

#### <u>ر</u>

# Datasheet Plomb Product code D879

Rev. 0 of 24/03/2023



#### ANTICORROSIVE TREATMENTS AND FINISHES

#### Washing

Spray treatment for removing oil and grease from metal surfaces using special degreasing liquids. Subsequent drying in dryer for 15 minutes.

#### Sandblasting

Manual sandblasting process with river sand, which increases the porosity of metal surfaces and thus the adhesion of thermosetting powders.

#### **Anti-corrosive application**

First painting cycle with an anticorrosive thermosetting powder primer based on epoxy resins and special pigments. It provides adequate protection against weathering.

#### **Anticorrosive polymerization**

Baking in an industrial curing oven at a temperature of 180°C. During this stage, the powder turns into a uniform, smooth and durable coating.

# Colored finish application

Final coating cycle with thermosetting powders. Application follows the same principles as the anticorrosive.

## Polymerization colored finish

Final baking in an industrial curing oven at a temperature of 180°C. The procedure follows the same principles as the curing of the anticorrosive. The powder is transformed into a uniform coating, and the surface appearance takes on the characteristics of the chosen color type, e.g. smooth, textured, wrinkled, etc.

Dimcar reserves the right to make, at any time, changes on the products deemed useful to improve the quality of the same; the images contained in the sheets may not faithfully reproduce the real colors of the items.

# Datasheet

# Plomb

## Product code D879

Rev. 0 of 24/03/2023



D	F	I١	/	F	R	٧

Product supplied already assembled with steel hardware and instructions for ground fixing.

**FIXING** 

The product is prepared for fixing to the ground using anchor bolts and expansion plugs.

**CORPORATE CERTIFICATIONS** 

#### ISO 9001:2015

Quality management system.

#### **UNI EN ISO 3834-3:2021**

Welding quality management system.

#### **Processing center**

Certificate of Processing Center