


Datasheet

Rainbow bike rack
Product code G495

Rev. 0 of 22/10/2024



1/5



DESCRIPTION









Structure

Consisting of a shaped base made of 8 mm thick galvanized sheet metal, obtained by laser cutting.

Seven shaped supports, made of 8 mm thick galvanized sheet metal, obtained by laser cutting, characterized by increasing shapes with a "rainbow" effect. Each support is equipped with a slotted hole for positioning the bicycle.

Total weight: 18Kg

COLOR FINISH AS PROVIDED IN THE CATALOG

| | | | |
|--|------------------------------|---|------------------------------|
|  | RAL 2000 (Bike support) |  | RAL 3020 (Bike support) |
|  | RAL 6019 (Bike support) |  | RAL 5012 (Bike support) |
|  | RAL 6017 (Bike support) |  | RAL 1018 (Bike support) |
|  | RAL 7016 (Basic) |  | RAL 4005 (Bike support) |

Customers can request a different finish from the RAL color options available on our website.

Datasheet

Rainbow bike rack
Product code G495

Rev. 0 of 22/10/2024



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

4/5



DELIVERY

The product comes with steel screws and fixing instructions.

FIXING

The product is designed to be fixed to the ground using expansion anchors and dowels.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 14 Jan 2008