
# Datasheet Aladino bin with lid Product code 318-BIS

Rev. 0 of 10/06/2016









Dimens has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

## Datasheet

## Aladino bin with lid Product code 318-BIS

Rev. 0 of 10/06/2016



**DESCRIPTION** 

#### Structure

The Aladino basket with lid is made up of a support upright in round galvanized steel tube Ø mm. 60x2, complete with PVC end cap with spherical head; shaped lid in galvanized steel sheet thickness mm. 3 and reinforcement bezel, in the upper part, obtained from high definition plasma cutting, in galvanized sheet. Lower arm for supporting the basket obtained from high definition plasma cutting, with decorative carvings, made of galvanized sheet thickness mm. 8.

- Cylindrical basket, made of galvanized steel sheet thickness mm. 1 with three full areas and two areas characterized by decorative rhomboidal and oblong inclined holes
- Upper part with anti-cut edge and shaped bottom in galvanized steel sheet thickness mm. 1.5 with holes for draining rainwater.

Overall weight: 10Kg

വ

Rev. 0 of 10/06/2016



### **COLOR FINISH AS PROVIDED IN THE CATALOG**



Customers can request a different finish from the RAL color options available on our website.

**PRODUCT OPTIONALS** 



Product code 431 - Ashtray Bond

**PRODUCT VARIANTS** 



Product code 318 - Bln Aladino

## Datasheet

Aladino bin with lid Product code 318-BIS

Rev. 0 of 10/06/2016



#### ANTICORROSIVE TREATMENTS AND FINISHES

#### Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

#### Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

### **Anticorrosive application**

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

### **Anticorrosive polymerization**

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

### Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

#### Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the article

## Datasheet

## Aladino bin with lid Product code 318-BIS

Rev. 0 of 10/06/2016



7	F	L	I١	1	F	R	١	1

The product comes with an assembly kit that includes steel screws and instructions for mounting and fixing.

**FIXING** 

The product must be installed by cementing.

**CORPORATE CERTIFICATIONS** 

#### ISO 9001:2015

Quality Management System.

### **UNI EN ISO 3834-3:2021**

Welding quality management system.

### **Processing center**

Certificate according to Italian Law D.M. of 14 Jan 2008

Ŋ