


Datasheet

Ashtray Cenerino with lid and mounting on existing pole

Product code 411

Rev. 0 of 10/06/2016



Datasheet

Ashtray Cenerino with lid and mounting on existing pole

Product code 411

Rev. 0 of 10/06/2016



DESCRIPTION

Structure

Cenerino ashtray with lid and with attachment to existing pole or bin consisting of a rear box made of 1.2 mm thick galvanized sheet metal with provision for attachment to existing pole. Shaped container made of 1.5 mm thick galvanized sheet metal with rounded edges on the front, complete with micro-perforated plate for extinguishing cigarettes, made of 1 mm thick polished AISI 304 stainless steel sheet.

- Shaped profile with container cover function in 1.5 mm thick galvanized sheet metal with front edging.
- Bottom in galvanized steel sheet with holes for draining rainwater.

Overall weight: 2Kg

Datasheet

Ashtray Cenerino with lid and mounting on existing pole

Product code 411

Rev. 0 of 10/06/2016



FINISH ACCORDING TO THE CATALOGUE



Rust
(Steel parts)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT VARIANTS



Product code 411-BIS - Cenerino ashtray with lid and column



Product code 411M -



Product code 411-M - Cenerino ashtrays with lid and wall mounting

Datasheet

Ashtray Cenerino with lid and mounting on existing pole

Product code 411

Rev. 0 of 10/06/2016



TREATMENTS AND FINISHES THAT PREVENT CORROSION

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

5/5

Dimcar si riserva di apportare, in qualsiasi momento, modifiche sui prodotti ritenute utili al miglioramento qualitativo degli stessi; le immagini contenute nelle schede potrebbero non riprodurre fedelmente i colori reali degli articoli.

Datasheet

Ashtray Cenerino with lid and mounting on existing pole

Product code 411

Rev. 0 of 10/06/2016



DELIVERY

Prodotto fornito già assemblato con viteria in acciaio ed istruzioni per il fissaggio.

FIXING

Il prodotto è dotato di staffa posteriore asolata per il fissaggio al palo esistente mediante fascette metalliche

CORPORATE CERTIFICATES

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 17 Jan 2018