





Dimcar si riserva di apportare, in qualsiasi momento, modifiche sui prodotti ritenute utili al miglioramento qualitativo degli stessi; le immagini contenute nelle schede potrebbero non riprodurre fedelmente i colori reali degli articoli.

DESCRIPTION

Structure

Clean model anti-terrorism bin for separate waste collection, consisting of a support upright in round tubular galvanized steel Ø mm. 60x2, and complete with PVC end cap.

- Circular plate, at the base, in galvanized sheet metal thickness mm. 4; the plate is provided with holes for fixing to the ground.
- Bag-holder rings consisting of No. 03 shaped lids, of the opening type, made of galvanized sheet metal thickness mm. 1.2 with anti-cut edging and plate indicating the type of collection.
- The lids are hinged to the bag-holder ring and are provided with a hole for inserting waste.
- Fixed internal bag-holder made of galvanized steel profile.

Overall weight: 9Kg

Datasheet

Bin Clean

Product code 326

Rev. 1 of 26/09/2016



FINISH ACCORDING TO THE CATALOGUE



Gun metal gray
(Support plate)



RAL 1018
("Plastic" collection ring)



RAL 9016
("Paper" collection ring)



RAL 5017
("Aluminum" collection ring)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT VARIANTS



Product code 326-M - Bin Clean with wall fixing

TREATMENTS AND FINISHES THAT PREVENT CORROSION

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

DELIVERY

Prodotto fornito in kit di assemblaggio con viteria in acciaio ed istruzioni per il montaggio e fissaggio.

FIXING

Il prodotto è predisposto per il fissaggio al suolo mediante tirafondi e tasselli ad espansione.

CORPORATE CERTIFICATES

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 17 Jan 2018