


Datasheet

Product code 298-I

Rev. 0 of 19/11/2025



1/5

DESCRIPTION

Structure

Clematis Inclusion bench, composed of four supports made of opposing arches made of 50x20x3 mm galvanized rectangular tubing, adorned with galvanized round bars.

- Seat and backrest frame made of 20x1.5 mm galvanized round steel tubing, complete with PVC ball-end caps.
- The seat consists of a central section designed for use by people with disabilities, with a backrest only, and two side sections with a seat and backrest.
-

The profiles on the seat and backrest are welded onto special 50x8 mm galvanized flat iron templates, giving it its anatomical shape.

- The bench features an "Inclusion" plaque positioned at the center of the backrest.

Total weight: 66 kg

FINISH ACCORDING TO THE CATALOGUE



Gun metal gray
(Steel parts)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT VARIANTS



Product code 298-A-150 - Clematis Rainbow bench of cm. 150



Product code 298-A-200 - Clematis Rainbow bench of cm. 200



Product code 298-BIS-V - Clematis bench curved outwards



Product code 298-D-150 - Clematis bench straight of cm. 150



Product code 298-D-200 - Clematis bench straight of cm. 200



Product code 298-GB - Clematis Grand Bouquet



Product code 298-R-150 - Clematis Ribbon bench of cm. 150



Product code 298-R-200 - Clematis Ribbon bench of cm. 200



Product code 298-V - Clematis bench curved inwards

TREATMENTS AND FINISHES THAT PREVENT CORROSION

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

DELIVERY

The product comes with an assembly kit that includes steel screws and instructions for mounting and fixing.

FIXING

The product is designed to be fixed to the ground using expansion anchors and dowels.

CORPORATE CERTIFICATES

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 17 Jan 2018