
Rev. 1 of 31/10/2019









Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

Datasheet

Cubik large trash bin Product code G490

Rev. 1 of 31/10/2019



DESCRIPTION

Struttra

With a particular square shape, consisting of two overlapping modules made with rounded corner panels in 3 mm thick galvanized steel sheet; Upper ring made of 3 mm thick galvanized steel sheet, with a tilting opening to facilitate the extraction of the internal container (bag supplied); at the base the basket is equipped with holes for draining rainwater and for fixing to the ground.

Overall weight: 40Kg

2

Rev. 1 of 31/10/2019



COLOR FINISH AS PROVIDED IN THE CATALOG



RAL 7001 (Lower module)



RAL 2000 (Upper module)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT OPTIONALS



Product code 431 - Ashtray Bond

PRODUCT VARIANTS



Product code G490-BIS - Cubik outdoor waste bin with lid

3/2

Datasheet

Cubik large trash bin Product code G490

Rev. 1 of 31/10/2019



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the article

Datasheet

Cubik large trash bin Product code G490

Rev. 1 of 31/10/2019



DELIVERY

The product comes with an assembly kit that includes steel screws and instructions for mounting and fixing.

FIXING

The product is designed to be fixed to the ground using expansion anchors and dowels.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 14 Jan 2008

2/2