


Datasheet

Bin Liberty with Lid
Product code 292-BIS

Rev. 0 of 10/06/2016



Datasheet

Bin Liberty whith Lid
Product code 292-BIS

Rev. 0 of 10/06/2016



DESCRIPTION

Structure

The Liberty basket with lid is made up of a support upright in round tube of galvanized steel Ø mm. 60x2 adorned in the upper part with a decorative frieze. Shaped lid in galvanized sheet metal thickness mm. 3, reinforcement bezel, in the upper part, provided with decorative carving made of galvanized sheet metal thickness mm. 8 and arm for supporting the basket with decorative element in galvanized flat iron.

- Cylindrical basket made with N. 37 profiles in round tube of galvanized steel Ø mm. 16x1.2; upper part edged with round tube of galvanized steel Ø mm. 20x1.5; shaped bottom in galvanized sheet metal thickness mm. 3 with holes for draining rainwater.

Overall weight: 22Kg

Datasheet

Bin Liberty whith Lid
Product code 292-BIS

Rev. 0 of 10/06/2016



FINISH ACCORDING TO THE CATALOGUE



Gun metal gray
(Steel components)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT OPTIONALS



[Product code 431 - Ashtray Bond](#)

PRODUCT VARIANTS



[Product code 292 - Bin Liberty](#)

TREATMENTS AND FINISHES THAT PREVENT CORROSION

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

Datasheet

Bin Liberty whith Lid
Product code 292-BIS

Rev. 0 of 10/06/2016



DELIVERY

Prodotto fornito in kit di assemblaggio con viteria in acciaio ed istruzioni per il montaggio e fissaggio.

FIXING

Il prodotto deve essere installato mediante cementazione.

CORPORATE CERTIFICATES

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 17 Jan 2018