



Datasheet

Snake litter bin with lid
Product code D826-BIS

Rev. 0 of 31/08/2022



Datasheet

Snake litter bin with lid
Product code D826-BIS

Rev. 0 of 31/08/2022



DESCRIPTION

Structure

What distinguishes the Snake bin is the sinuosity of its shape, characteristic of the snake; the upright support is made of tubular profiles of galvanized steel with a square section of mm. 60x60, shaped in the lower part. In the upper part, the bin is equipped with a shaped lid, made of galvanized sheet metal. Square-shaped basket barrel, made of shaped panels of galvanized sheet metal, equipped with an upper ring with a reduced hole for the introduction of waste, made of galvanized sheet metal, thickness mm. 3.

The barrel is characterized by stylised decorative shapes, obtained by laser cutting and made of galvanized sheet metal, thickness mm. 2.

Overall weight: 26Kg

Datasheet

Snake litter bin with lid
Product code D826-BIS

Rev. 0 of 31/08/2022



COLOR FINISH AS PROVIDED IN THE CATALOG



RAL 8012
(Decorative panels)



RAL 1015
(Uprights, basket drum and ring)

Customers can request a different finish from the RAL color options available on our website.

PRODUCT OPTIONALS



[Product code 431 - Ashtray Bond](#)

PRODUCT VARIANTS



[Product code D826 - Snake litter bin](#)

Datasheet

Snake litter bin with lid
Product code D826-BIS

Rev. 0 of 31/08/2022



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

4/5

Datasheet

Snake litter bin with lid
Product code D826-BIS

Rev. 0 of 31/08/2022



DELIVERY

The product comes with an assembly kit that includes steel screws and instructions for mounting and fixing.

FIXING

The product must be installed by cementing.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 14 Jan 2008