
Rev. 0 of 21/06/2023









Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the articles

/2

Datasheet

Temperarifiuti
Product code D872

Rev. 0 of 21/06/2023



DESCRIPTION

Structure

Temperarifiuti model waste bin, a new form of furniture with an unmistakable style, designed for use by children. Playful lines and bright colors, all child-friendly. The waste bin is made of a single shaped box, with the characteristic "pencil sharpener" shape, made of 2 mm thick galvanized sheet metal, with front/back panels shaped with laser cutting technology, and side panels shaped by pressbending.

- Upper door with a circular hole, reminiscent of the insertion of the pencil, for the introduction of waste, made of 2 mm thick galvanized sheet metal.
- 2. Front metal profile, shaped in the shape of a "blade", made of 2 mm thick galvanized sheet metal.
- 2. The waste bin is equipped with a metal container inside for the insertion of any bag (not supplied).
- Base equipped with feet with plastic end caps, and internal bottom equipped with holes for fixing to the ground.

Overall weight: 31Kg

Ŋ

Datasheet Temperarifiuti Product code D872

Rev. 0 of 21/06/2023

COLOR FINISH AS PROVIDED IN THE CATALOG





Customers can request a different finish from the RAL color options available on our website.

3/2

Datasheet

Temperarifiuti
Product code D872

Rev. 0 of 21/06/2023



ANTICORROSIVE TREATMENTS AND FINISHES

Washing

Spray treatment is used to get rid of oils and fats from metal surfaces by using special degreasing liquids. The process involves drying in a dryer for 15 minutes.

Sandblasting

The porosity of metal surfaces is increased by the manual sandblasting process with river sand, which results in an increase in thermosetting powder adhesion.

Anticorrosive application

The first step in the coating process involves using a thermosetting powder anti-corrosion base made of epoxy resins and specific pigments. It provides enough protection against the elements.

Anticorrosive polymerization

The process involves cooking in an industrial curing oven at 180°C. In this step, the powder is transformed into a coating that is uniform, smooth, and lasting.

Polymerization coloured finish

The final phase of coating with thermosetting powders. The application complies with the same principles as the anti-corrosion.

Polymerization colored finish

The final product will be cured in an industrial curing oven at a temperature of 180°C. The procedure is based on the same principles as the polymerization of the anti-corrosion agent. The powder becomes a uniform coating, and the surface becomes the characteristics of the chosen color type, including smooth, peeled, or wrinkled, etc.

Dimcar has the authority to make changes to the products that are useful for improving their quality. The images on the cards may not accurately portray the actual colors of the article

Datasheet

Temperarifiuti Product code D872

Rev. 0 of 21/06/2023



The product comes with steel screws and fixing instructions.

FIXING

The product is designed to be fixed to the ground using expansion anchors and dowels.

CORPORATE CERTIFICATIONS

ISO 9001:2015

Quality Management System.

UNI EN ISO 3834-3:2021

Welding quality management system.

Processing center

Certificate according to Italian Law D.M. of 17 Jan 2018

Ŋ